



Castrol Optileb™ GR 823 Range

Food Machinery Greases

Description

Castrol Optileb™ GR 823 greases (previously called Molub-Alloy™ Foodproof 823 FM) were developed for general lubrication of food machinery. They have been approved as "physiologically safe" by the Landesgewerbe-Anstalt LGA Bayern.

Optileb GR 823 greases have also been approved by the U.S. Department of Agriculture (NSF) as "H1" lubricants which can be used in the food and beverage industry even if incidental contact with food products is possible.

- A select base oil blend plus an FDA approved thickener provide good adhesion, film strength and water-wash resistance even at elevated temperatures. Drip-free characteristics and the off-white color of Optileb GR 823 greases complement house keeping efforts in food and kindred industries.
- A high performance combination of food grade additives provides excellent anti-wear protection. The combination of additives and blending techniques maximize rust and oxidation characteristics for effective rust protection and long service life of the grease.

Application

- Developed to lubricate food machinery in high-temperature applications where incidental contact with food is possible.
- They are recommended for sleeve and rolling bearings in overhead conveyors and other material handling equipment.
- May be applied manually or with automatic dispensing equipment.
- Lighter consistency GR 823-0 grease can be used in gear cases where a non-channeling slump grease is needed to control leakage.
- Temperature application range: - 30°C up to - 120°C

Advantages

- H1 lubricants acceptable for use where incidental contact with food is possible.
- Very high melting point and non-drip characteristics of this grease minimize product contamination.
- Unique water resistance provides continuous protection even when equipment is washed down periodically.
- Physiologically safe (approved by LGA Bayern) - base fluid and all other ingredients used in GR 823 comply with sections 178.3570 and 178.3620 of the FDA guidelines.

Typical Characteristics

Name	Method	Units	823-0	823-1	823-2
Thickener type	-	-	Aluminium Complex	Aluminium Complex	Aluminium Complex
Worked Penetration (60 strokes @ 25°C / 77°F)	ASTM D217 / ISO 2137	0.1 mm	355 - 385	310 - 340	265 - 295
Dropping point	ASTM D566 / ISO 2176	°C/°F	-	>230/>446	>230/>446
Base Oil Viscosity @ 40°C / 104°F	ASTM D445 / ISO 3104	mm ² /s	192	192	192
Base Oil Viscosity @ 100°C / 212°F	ASTM D445 / ISO 3104	mm ² /s	17.5	17.5	17.5
Flash Point - open cup method	ASTM D92 / ISO 2592	°C/°F	>200/>392	>200/>392	>200/>392
Water Resistance	DIN 51807-1	Rating	0	0	0
FE-9 Bearing Life test - A/ 1500/ 6000-120	DIN 51821-2	Pass	Pass	Pass	Pass
Copper Corrosion (24 hrs, 100°C / 212°F)	ASTM D4048	Rating	1	1	1
Rust Test - EMCOR (distilled water)	ASTM D6138 / ISO 11007	Rating	0/0	0/0	0/0
Roll Stability test - Shear Stability (5 hrs, 70°C / 158°F)	ASTM D1831 (modified)	Change %	≤ 10	≤ 10	≤ 10
Four Ball Wear test - Wear Scar Diameter	DIN 51350-5D	mm	<0.60	<0.60	<0.60
Flow pressure @ -20°C / - 4°F	DIN 51805	mBar	<250	<350	550

Additional Information

- Optileb GR 823 greases should not be mixed with greases using a different thickener. Lubrication intervals should be increased gradually to ensure complete removal of previous lubricant.
- At higher temperatures (above 100°C) relubrication intervals should be established by inspection.

This product was previously called Molub-Alloy™ Foodproof 823 FM . The name was changed in 2015

Castrol Optileb™ GR 823 Range

07 Apr 2015

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

BP Lubricants USA Inc., 1500 Valley Road, Wayne, NJ 07470
 Telephone: +1-888-CASTROL Product Information: +1-877-641-1600
www.castrol.com/en_us/b2b/home.html