



广州孚润 400-992-6811

A silica thickened, medium viscosity, synthetic hydrocarbon grease intended for sliding, bearing and gear train applications. Regulations require that any addition to food not exceed 10 parts per million.

NSF H-1 Registered #128785

	Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)			-35 to 120	
Thickener			Silica	
Base Oil	Туре		Polyalphaolefin	
	Kinematic Viscosity	40°C	194 cSt	
		100°C	22.8 cSt	
	Viscosity Index		152	ASTM D-2270
	Flash Point	°C	235	ASTM D-92
	Pour Point	°C	-40	ASTM D-97
	Typical Properties of	the	Typical Value	Test Method
	Grease			
Color, Appearance			Clear, Smooth	
Penetration	NLGI Grade		2	ASTM D-217
(1/10 mm)	Worked	60X	291	ASTM D-217
	Unworked		272	ASTM D-217
Density		25°C	0.88 g/cm ³	NYE CTM
Oil Separation	24 hour(s)	100°C	2	ASTM D-6184
Evaporation	24 hour(s)	100°C	0.2 %	ASTM D-972
		100°C	0	

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (2001)