FLUOROCARBON GEL 880



广州孚润 400-992-6811

NSF H-1 Approved: Registration #133065

A PTFE-thickened, heavy viscosity dimethyl silicone grease with excellent water resistance and mechanical stability under a wide temperature range. Suitable for use on machinery and instrumentation where incidental contact with food is possible.

NSF H1 Registered # 133065

	Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)			-40 to 200	
Thickener			PTFE	
Base Oil	Туре		Dimethyl Silicone	
	Kinematic Viscosity	100°C	7349 cSt	ASTM D-445
		40°C	18407 cSt	
	Viscosity Index		658	
	Flash Point	°C	350	ASTM D-92
	Pour Point	°C	-62	ASTM D-97
	Typical Properties of	the	Typical Value	Test Method
	Grease			
Color, Appearance			White, Smooth	
Penetration	Unworked		287	ASTM D-217
(1/10 mm)	Worked	60X	277	
	NLGI Grade		2	
Density		25°C	1.25 g/cm ³	NYE CTM
Oil Separation	24 hour(s)	100°C	0	ASTM D-6184
Evaporation	24 hour(s)	100°C	0.08	NYE CTM

Caution - Careful design and procedures are required for automated, high pressure dispensing of high viscosity lubricants. High pressures with entrained air and impeded flow can cause dieseling. Please contact Nye Technical Services for additional information.

Caution - Careful design and procedures are required for automated, high pressure dispensing of high viscosity lubricants. High pressures with entrained air and impeded flow can cause dieseling. Please contact Nye Technical Services for additional information. (1504)