

A silica thickened, medium viscosity, synthetic hydrocarbon grease for lubrication and protection of electrical contacts. Benefits include good water resistance.

Ford: WSB-M1C239-A, GM: 9986087, DaimlerChrysler: MS-9469

Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)		-40 to 135	
Thickener		Silica	
Base Oil	Type	Polyalphaolefin	
	Kinematic Viscosity	100°C	39.4 cSt
		40°C	400 cSt
		-30°C	213788.5 cSt
	Viscosity Index		147.5
	Flash Point	°C	321
	Pour Point	°C	-36
Typical Properties of the Grease		Typical Value	Test Method
Color, Appearance		Water White, Smooth	
Penetration (1/10 mm)	Unworked		266
	Worked	60X	286
		10K	303
		100K	311
	NLGI Grade		2
Density		25°C	0.88
Oil Separation	24 hour(s)	100°C	1.5 %
Evaporation	24 hour(s)	100°C	0.3

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (2001)