

RHEOLUBE 362

广州孚润 400-992-6811

A lithium soap thickened synthetic hydrocarbon grease designed for bearings, sliding surfaces, gear trains and electrical components.

DaimlerChrysler: MS-9914: Ford: ESH-M1C205A

	Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)			-54 to 125	
Thickener	-		Lithium Soap	
Base Oil	Туре		Polyalphaolefin	
	Kinematic Viscosity	100°C	6 cSt	ASTM D-445
		40°C	30 cSt	
	Viscosity Index		141	ASTM D-2270
	Flash Point	°C	235	ASTM D-92
	Pour Point	°C	-63	ASTM D-97
	Typical Properties of	the	Typical Value	Test Method
	Grease			
Color, Appearance			Tan, Smooth	
Penetration	Worked	60X	278	ASTM D-217
(1/10 mm)	Unworked		267	
	NLGI Grade		2	
	Worked	10k	319	
Density		25°C	0.88 g/cm ³	NYE CTM
Oil Separation	24 hour(s)	100°C	3.02	ASTM D-6184
Evaporation	24 hour(s)	100°C	0.07	

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (2001)

Nye Lubricants