## **NYOGEL 795LT**



广州孚润 400-992-6811

A silica thickened, light viscosity, synthetic hydrocarbon grease intended for applications requiring wide temperature serviceability, plastic compatibility and good mechanical stability.

	Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)			-40 to 125	
Thickener			Silica	
Base Oil	Туре		Polyalphaolefin	
	Kinematic Viscosity	40°C	2100 cSt	
		100°C	138 cSt	
	Viscosity Index		164	ASTM D-2270
	Flash Point	°C	248	ASTM D-92
	Typical Properties of	the	Typical Value	Test Method
	Grease			
Color, Appearance			Light Yellow, Smooth	
Penetration	Worked	60X	277	ASTM D-217
(1/10 mm)	Unworked		256	ASTM D-217
	NLGI Grade		2	ASTM D-217
Density		25°C	0.83 g/cm <sup>3</sup>	NYE CTM
Oil Separation	24 hour(s)	100°C	1.2	ASTM D-6184
Evaporation	24 hour(s)	100°C	0.2	

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product.

(1409)