

FLUOROCARBON GEL 880FG 广州孚润 400-992-6811

A PTFE-thickened, heavy viscosity dimethyl silicone grease with excellent water resistance and mechanical stability under a wide temperature range. Suitable for use on machinery and instrumentation where incidental contact with food is possible.

NSF H1 & IFANCA Halal Certified & NSF-61, ACS, WRAS potable water approved

	Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)			-40 to 200	
Thickener			PTFE	
Base Oil	Туре		Dimethyl Silicone	
	Kinematic Viscosity	100°C	7349 cSt	
		40°C	18407 cSt	
	Flash Point	C°	>300	ASTM D-92
	Pour Point	C°	-62	ASTM D-97
	Typical Properties of	the	Typical Value	Test Method
	Grease			
Color, Appearance			White, Smooth	
Penetration	Unworked		287	ASTM D-217
(1/10 mm)	Worked	60	277	ASTM D-217
	NLGI Grade		2	ASTM D-217
Density		25°C	1.25 g/cm ³	NYE CTM
Oil Separation	24 hour(s)	100°C	0	ASTM D-6184
Evaporation	24 hour(s)	121°C	0.06	NYE CTM

Caution - Careful design and procedures are required for automated, high pressure dispensing of high viscosity lubricants. High pressures with entrained air and impeded flow can cause dieseling. Please contact Nye Technical Services for additional information.

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1710)