



广州孚润 400-992-6811

Rust Inhibited

A mildly thixotropic, silica thickened, heavy viscosity, synthetic hydrocarbon grease intended for worm drives, open gears or unsealed gear boxes where gear oils cannot be used. Benefits include high film strength over a wide temperature range.

	Lubricant Properties	5	Typical Value	Test Method
Recommended Service Range (°C)		-20 to 125		
Thickener			Silica	
Base Oil	Туре		PAO/Polybutene	
	Kinematic Viscosity	100°C	33 cSt	ASTM D-445
		40°C	291 cSt	
	Viscosity Index		157.5	ASTM D-2270
	Flash Point	°C	239	ASTM D-92
	Pour Point	°C	-38	ASTM D-97
	Typical Properties o	of the	Typical Value	Test Method
	Grease			
Color, Appearance			Light yellow	
Penetration	Worked	60X	298	ASTM D-217
(1/10 mm)	Unworked		285	
	Worked	10,000X	314	
	NLGI Grade		1.5	
Density		25°C	0.88 g/cm ³	NYE CTM
Oil Separation	24 hour(s)	100°C	2	ASTM D-6184
Evaporation	24 hour(s)	100°C	0.3	NYE CTM

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (2001)