

A PTFE thickened, light viscosity, completely fluorinated grease possessing very wide temperature capability, excellent plastic and elastomer compatibility and resistance to aggressive chemicals.

DaimlerChrysler: MS-9987, GM: 9985880

Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)		-45 to 225	
Thickener		PTFE	
Base Oil	Type	Perfluoropolyether	
	Kinematic Viscosity	100°C 40°C	18 cSt 167 cSt
	Viscosity Index		120
	Flash Point	°C	> 300
	Pour Point	°C	-48
			ASTM D-445
			ASTM D-2270
			Cleveland Open Cup
			ASTM D-97
Typical Properties of the Grease		Typical Value	Test Method
Color, Appearance		White, Smooth	
Penetration (1/10 mm)	Unworked	259	ASTM D-217
	NLGI Grade	2	
	Worked	60X 278	
Density	25°C	1.96 g/cm3	NYE CTM
Oil Separation	24 hour(s)	100°C	3.8
Evaporation	24 hour(s)	150°C	0.23 %
			ASTM D-6184
			ASTM D-972

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1510)