

Copper Deactivator

A PTFE thickened, medium viscosity, completely fluorinated grease possessing very wide temperature capability, excellent plastic and elastomer compatibility and resistance to aggressive chemicals

Lubricant Properties		Typical Value	Test Method	
Recommended Service Range (°C)		-45 to 225		
Thickener		PTFE		
Base Oil	Type	Perfluoropolyether		
(Uniflor 8170)	Kinematic Viscosity	100°C	18 cSt	ASTM D-445
		40°C	167 cSt	ASTM D-445
		-40°C	800000 cSt	ASTM D-445
	Viscosity Index		120	ASTM D-2270
	Flash Point	°C	None, Non-Flammable	ASTM D-92
	Pour Point	°C	-48	ASTM D-97
Typical Properties of the Grease		Typical Value	Test Method	
Color, Appearance		White, Smooth		
Penetration (1/10 mm)	Unworked		281	ASTM D-217
	Worked	60	287	ASTM D-217
	NLGI Grade		2	ASTM D-217
Density	25°C	1.96 g/cm ³	NYE CTM	

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1408)