

## Rust Inhibited

A PTFE thickened, heavy viscosity, completely fluorinated grease for use in high temperature applications exposed to fuels or aggressive chemicals. It possesses excellent thermo-oxidative stability and low vapor pressure characteristics.

Lubricant Properties		Typical Value	Test Method	
<b>Recommended Service Range (°C)</b>		-65 to 250		
<b>Thickener</b>		PTFE		
<b>Base Oil</b>	Type	Perfluoropolyether		
<b>(Uniflor 8920)</b>	Kinematic Viscosity	100°C	45 cSt	ASTM D-445
		40°C	150 cSt	ASTM D-445
	Viscosity Index		340	ASTM D-2270
	Flash Point	°C	300	ASTM D-92
	Pour Point	°C	-65	ASTM D-97
Typical Properties of the Grease		Typical Value	Test Method	
<b>Color, Appearance</b>		White		
<b>Penetration (1/10 mm)</b>	Unworked	269	ASTM D-217	
	Worked	60 X	295	ASTM D-217
	NLGI Grade		2	ASTM D-1403
<b>Density</b>	25°C	1.89 g/cm <sup>3</sup>	NYE CTM	
<b>Oil Separation</b>	24 hour(s)	100°C	4.7 %	ASTM D-6184
<b>Evaporation</b>	24 hour(s)	100°C	0 %	

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product MSDS for detailed safety information because this product. (1402)