

Rust Inhibited

A light viscosity synthetic hydrocarbon oil intended for reduction or prevention of fretting corrosion

| Lubricant Properties | | Typical Value | Test Method | |
|---------------------------------------|---------------------|-----------------|------------------------|-------------|
| Recommended Service Range (°C) | | -54 to 120 | | |
| Color, Appearance | | Light yellow | | |
| Base Oil | Type | Polyalphaolefin | | |
| | Kinematic Viscosity | 40°C | 29.7 cSt | |
| | | 100°C | 5.7 cSt | |
| | Viscosity Index | 136 | ASTM D-2270 | |
| | Flash Point | °C | 238 | ASTM D-92 |
| | Pour Point | °C | -62 | ASTM D-97 |
| Evaporation | 24 hour(s) | 100°C | 0.1 | |
| Density | | 25°C | 0.83 g/cm ³ | ASTM D-1480 |

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1407)