

RHEOLUBE 786B

广州孚润 400-992-6811

Rust Inhibited, Tackifier

A stiff, lithium soap thickened, heavy viscosity, diester grease intended for heavy duty instrument, switch gear and similar applications where high temperature stability is required.

	Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)			-20 to 150	
Thickener			Lithium Soap	
Base Oil	Туре		Ester	
	Kinematic Viscosity	100°C	110 cSt	ASTM D-445
		40°C	660 cSt	ASTM D-445
	Viscosity Index		131	ASTM D-2270
	Flash Point	°C	225	ASTM D-92
	Pour Point	°C	-32	ASTM D-97
	Typical Properties of t	the	Typical Value	Test Method
	Grease			
Color, Appearance			Light Amber, Smooth	
Penetration	Unworked		221	ASTM D-217
(1/10 mm)	Worked	60X	257	ASTM D-217
Density		25°C	0.94 g/cm ³	NYE CTM
Oil Separation	24 hour(s)	100°C	0	ASTM D-6184
Evaporation	24 hour(s)	100°C	1.3 %	ASTM D-972

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1408)