

A medium viscosity, completely fluorinated oil possessing very wide temperature capability, excellent oxidation resistance, excellent plastic and elastomer compatibility and resistance to aggressive chemicals.

NSF H1 Approved: Registration #142527

Lubricant Properties		Typical Value	Test Method	
Recommended Service Range (°C)		-65 to 250		
Color, Appearance		Clear		
Base Oil	Type	Perfluoropolyether		
	Kinematic Viscosity	40°C	150 cSt	
		100°C	45 cSt	
	Viscosity Index		340	ASTM D-2270
	Flash Point	°C	None, Non-Flammable	ASTM D-92
	Pour Point	°C	-65	ASTM D-97
Evaporation	24 hour(s)	150°C	0.01 %	ASTM D-972
Density		25°C	1.88 g/cm ³	ASTM D-1480

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1509)