

## UV Tracer

A 20% dispersion of a synthetic hydrocarbon lubricant in an isoparaffinic solvent intended as a general purpose lubricant for tin/lead connectors.

Typical Properties of the Oil		Typical Value	Test Method	
<b>Recommended Service Range (°C)</b>		-40 to 120		
<b>Base Oil</b>	Type	Polyalphaolefin		
	Kinematic Viscosity	40°C	1015 cSt	
		100°C	77 cSt	
	Viscosity Index	158	ASTM D-2270	
	Flash Point	°C	40	ASTM D-92
	Pour Point	°C	-29	ASTM D-97
	Density	25°C	0.85 g/cm <sup>3</sup>	ASTM D-1480
	Evaporation	24 hour(s) 150°C	1 %	NYE CTM
Typical Properties of the Grease		Typical Value	Test Method	
<b>Color, Appearance</b>		light yellow		
<b>Penetration (1/10mm)</b>	Unworked	> 300	ASTM D-217	
<b>Thickener</b>		Silica		
<b>Density</b>	25°C	0.89 g/cm <sup>3</sup>	NYE CTM	
<b>Dropping Point</b>		> 260 (non-melting)	ASTM D-2265	
<b>Oil Separation</b>	24 hour(s)	66°C	4	FTM 791, Method 321.2
<b>Evaporation</b>	24 hour(s)	150°C	1 %	ASTM D-972
Typical Properties of the Solvent		Typical Value	Test Method	
<b>Chemical Composition</b>		Isoparaffinic		
<b>Concentration by Weight</b>		80 %		
<b>Flash Point</b>		°C	40	ASTM D-92
<b>Boiling Point</b>		°C	156	ASTM D-92
<b>Density</b>		25°C	0.75 g/cm <sup>3</sup>	ASTM D-1480

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1507)