

## Rust Inhibited

A PTFE thickened, medium viscosity, perfluoropolyether grease intended for high temperature rolling element bearings and electrical contacts exposed to aggressive atmospheres, temperature extremes, fuels or aggressive chemicals.

Lubricant Properties			Typical Value	Test Method
<b>Recommended Service Range (°C)</b>			-70 to 225	
<b>Thickener</b>			PTFE	
<b>Base Oil</b>	Type		Perfluoropolyether	
<b>(Uniflor 8910)</b>	Kinematic Viscosity	100°C	30 cSt	ASTM D-445
		40°C	90 cSt	ASTM D-445
		-40°C	3100 cSt	ASTM D-445
	Viscosity Index		340	ASTM D-2270
	Pour Point	°C	-70	ASTM D-97
Typical Properties of the Grease			Typical Value	Test Method
<b>Color, Appearance</b>			Off-White, Smooth	
<b>Penetration (1/10 mm)</b>	Worked	60X	299	ASTM D-217
	Unworked		374	ASTM D-217
<b>Density</b>		25°C	1.9 g/cm <sup>3</sup>	ASTM D-70
<b>Oil Separation</b>	24 hour(s)	100°C	6.2	ASTM D-6184
<b>Evaporation</b>	24 hour(s)	100°C	0 %	NYE CTM

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1505)