RHEOLUBE 731



广州孚润 400-992-6811

A soft, lithium soap thickened, heavy viscosity, polyglycol grease intended for arcing and non-arcing switch mechanisms. Fortified with a novel additive intended to reduce contact resistance by scavenging surface oxides.

	Lubricant Properties		Typical Value	Test Method
Recommended Servi	ce Range (°C)		-30 to 100	
Thickener			Lithium Soap	
Base Oil	Туре		Polyglycol	
(Synthetic Oil 327A)	Kinematic Viscosity	100°C	54 cSt	ASTM D-445
		40°C	375 cSt	ASTM D-445
	Viscosity Index		212	ASTM D-2270
	Flash Point	°C	183	ASTM D-92
	Pour Point	°C	-20	ASTM D-97
	Typical Properties of the		Typical Value	Test Method
	Grease			
Color, Appearance			Tan to Light Tan, Smooth	
Penetration	Unworked		318	ASTM D-217
(1/10 mm)	Worked	60X	324	ASTM D-217
	NLGI Grade		1	ASTM D-217
Density		25°C	0.99 g/cm ³	ASTM D-1480
Oil Separation	24 hour(s)	100°C	5.1	ASTM D-6184
Evaporation	24 hour(s)	100°C	2 %	NYE CTM

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1409)