



广州孚润 400-992-6811

Rust Inhibited

A lithium soap thickened, light viscosity, synthetic hydrocarbon grease intended for bearings, sliding surfaces, gear trains, and switchgear. Excellent for wide temperature performance.

| | Lubricant Properties | | Typical Value | Test Method |
|--------------------------------|-----------------------|-------|------------------------|-------------|
| Recommended Service Range (°C) | | | -54 to 125 | |
| Thickener | | | Lithium Soap | |
| Base Oil | Туре | | Polyalphaolefin | |
| | Kinematic Viscosity | 100°C | 8.6 cSt | ASTM D-445 |
| | | 40°C | 52 cSt | |
| | Viscosity Index | | 144 | ASTM D-2270 |
| | Flash Point | °C | 240 | ASTM D-92 |
| | Pour Point | °C | -60 | ASTM D-97 |
| | Typical Properties of | the | Typical Value | Test Method |
| | Grease | | | |
| Color, Appearance | | | Light Tan, Smooth | |
| Penetration | NLGI Grade | | 2 | ASTM D-217 |
| (1/10 mm) | Worked | 60X | 280 | |
| | | 100K | 360 | |
| | Unworked | | 261 | |
| Density | | 25°C | 0.87 g/cm ³ | NYE CTM |
| Oil Separation | 24 hour(s) | 100°C | 3 % | ASTM D-6184 |
| Evaporation | 24 hour(s) | 100°C | 0.08 | NYE CTM |

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1508)