## **UNIFLOR 8921SU**



广州孚润 400-992-6811

## **UV Tracer**

A very soft PTFE thickened, heavy viscosity, completely fluorinated grease for use in high temperature applications exposed to fuels or aggressive chemicals. It possesses excellent thermo-oxidative stability and low vapor pressure characteristics.

	Lubricant Properties		Typical Value	Test Method
Recommended Serv	ice Range (°C)		-65 to 250	
Thickener			PTFE	
Base Oil	Туре		Perfluoropolyether	
(Uniflor 8920)	Kinematic Viscosity	100°C	45 cSt	ASTM D-445
		40°C	150 cSt	ASTM D-445
		-40°C	4300 cSt	ASTM D-445
	Viscosity Index		340	ASTM D-2270
	Flash Point	°C	None, Non-Flammable	ASTM D-92
	Pour Point	°C	-65	ASTM D-97
	Typical Properties of the		Typical Value	Test Method
	Grease			
Color, Appearance			White	
Penetration	Unworked		357	
(1/10 mm)	NLGI Grade		0	
Density		25°C	1.89 g/cm <sup>3</sup>	ASTM D-70
Oil Separation	100 hour(s)	24°C	8.7 %	FTM 791,
				Method 321.2
Evaporation	24 hour(s)	100°C	0 %	NYE CTM

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product MSDS for detailed safety information because this product. (1402)