

A PTFE thickened, medium viscosity, completely fluorinated grease for use in high temperature applications exposed to fuels or aggressive chemicals. It possesses excellent thermo-oxidative stability and low vapor pressure characteristics.

Ford: WSB-M1C242-A, GM: 9986173

Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)		-50 to 225	
Thickener		PTFE	
Base Oil	Type	Perfluoropolyether	
(Uniflor 8510)	Kinematic Viscosity	100°C	15.8 cSt
		40°C	65 cSt
	Viscosity Index		258
	Pour Point	°C	-54
		ASTM D-445	ASTM D-97
Typical Properties of the Grease		Typical Value	Test Method
Color, Appearance		White, Smooth	
Penetration (1/10mm)	Worked	60X	281
			ASTM D-217
Density		25°C	1.95 g/cm ³
			NYE CTM
Oil Separation	24 hour(s)	150°C	6.8
			ASTM D-6184
Evaporation	24 hour(s)	150°C	1 %
			NYE CTM

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1504)