

# Anti-Seize High-Tech Assembly Paste



Sulfur content (DIN 514)	<0,1 %
Water resistance (DIN 51807)	1 - 90
Pressure (DIN 53281-83)	230 N/mm <sup>2</sup>
Salt spray test	> 170 h
Specific resistance	1,0 x 10 <sup>15</sup> Ohm/cm
Temperature resistance	-40 to +1.400 °C
ISSA-Code	53.402.81/82/83/84/85/86/87/88/89
IMPA-Code	450882/83/84/85/86/87

## reliable protection against corrosion seizing and cold welding metal-free NSF approval

Anti-Seize "High-Tech" is high temperature resistant, has excellent separating characteristics, is metal-free, neutral to materials and has an NSF approval.

Anti-Seize „High-Tech“ is particularly suitable when metal-containing pastes can cause electrolytic reactions, when nickel-containing products should or may not be used due to health reasons and when dark metalcontaining products should or may not be used for optical reasons.



## Technical Data

Basic Oil	medicinal oil
Colour	white
Density at +20°C (+68°F) (DIN 51757)	1,42 g/cm <sup>3</sup>
OFW device coefficient of friction	0,10 - 0,13
Friction total	0,13 μ
Friction thread	0,11 μ
Friction head bottom	0,14 μ
VKA-TEST (DIN 51350) goods load	3.600 N
VKA-TEST (DIN 51350) welding load	3.800 N
VKA-TEST (DIN 51350) Spherical cap value (1Min/1000N)	0,7 mm
Worked penetration ( DIN ISO 2137)	310 - 340 1/10 mm
Specific heat transfer capacity (20°C)	1,574 J/(g·K)
Thermal diffusivity (20°C)	0,302 mm <sup>2</sup> /s
Thermal conductivity (ISO 22007-4) (20°C)	0,675 W/m·K
Dielectric strength (DIN EN 60243-1) (20°C)	6,3 kV/mm

### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

## Surface pre-treatment

Clean and degrease surfaces. Apply the assembly paste evenly. AS is suitable only for assembly paste specific applications, it does not replace pure lubricants and greases.

## Processing

Apply a good quantity of Assembly Paste with a brush, cloth or plastic sponge. On threads it is important that Assembly Paste is applied down to the thread root to ensure a good sealing effect. Assembly Paste must not be mixed with greases or oils to avoid changes in the material characteristics. WEICON Assembly Pastes do not replace oil or grease lubrication.

## Storage

Keep container tightly closed. Do not store together with oxidizing agents. Store in a dry place at storage temperature. Original container are storable for 24 months.

## Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

## Available sizes:

26100005	Anti-Seize High-Tech Assembly Paste 5 g
26100003	Anti-Seize High-Tech Assembly Paste 30 g
26100085	Anti-Seize High-Tech Assembly Paste 85 g
26100012	Anti-Seize High-Tech Assembly Paste 120 g
26100040	Anti-Seize High-Tech Assembly Paste 400 g
26100045	Anti-Seize High-Tech Assembly Paste 450 g
26100050	Anti-Seize High-Tech Assembly Paste 500 g
26100100	Anti-Seize High-Tech Assembly Paste 1.0 kg
26100180	Anti-Seize High-Tech Assembly Paste 1.8 kg
26100500	Anti-Seize High-Tech Assembly Paste 5.0 kg
26100910	Anti-Seize High-Tech Assembly Paste 10.0 kg
26100920	Anti-Seize High-Tech Assembly Paste 20.0 kg

## Accessories:

10953001	Processing Spatula,
10953003	Processing Spatula,

WEICON GmbH & Co. KG  
 (Headquarters)  
 Germany  
 phone +49 (0) 251 9322 0  
 info@weicon.de  
 www.weicon.de

WEICON Middle East L.L.C.  
 United Arab Emirates  
 phone +971 4 880 25 05  
 info@weicon.ae  
 www.weicon.ae

WEICON Inc.  
 Canada  
 phone +1 877 620 8889  
 info@weicon.ca  
 www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.  
 Turkey  
 phone +90 (0) 212 465 33 65  
 info@weicon.com.tr  
 www.weicon.com.tr

WEICON Romania SRL  
 Romania  
 phone +40 (0) 3 65 730 763  
 office@weicon.com  
 www.weicon.com.ro

WEICON SA (Pty) Ltd  
 South Africa  
 phone +27 (0) 21 709 0088  
 info@weicon.co.za  
 www.weicon.co.za

WEICON South East Asia Pte Ltd  
 Singapore  
 phone (+65) 6710 7671  
 info@weicon.com.sg  
 www.weicon.com.sg

WEICON Czech Republic s.r.o.  
 Czech Republic  
 phone +42 (0) 417 533 013  
 info@weicon.cz  
 www.weicon.cz

WEICON Ibérica S.L.  
 Spain  
 phone +34 (0) 914 7997 34  
 info@weicon.es  
 www.weicon.es

WEICON Italia S.r.l.  
 Italy  
 phone (+39) 0102924871  
 info@weicon.it  
 www.weicon.it